

**Product Information:**


# Silicone Remover 911

**Removes cured and uncured silicone sealant**

**General description & application:**

*Silicone Remover 911 removes cured and uncured silicone sealant on most materials and leaves completely silicone free surfaces. The Silicone Remover is also suitable for removing small areas with mould fungus on silicone sealant.*

*Silicone Remover 911 can be used on wood (treated and untreated), brickwork, gypsum board, concrete, glass, enamel, china, metals (e.g. copper, brass, zinc, galvanised steel and aluminium), artificial materials (e.g. acrylic (plexiglass), polycarbonate, glass fibre and PVC). On other surfaces a test should be carried out.*

Member of  Danish Association of Sealant Applicators & Manufacturers.



*Silicone Remover 911 removes cured and uncured silicone sealant on most materials and leaves completely silicone free surfaces. The Silicone Remover is also suitable for removing small areas with mould fungus on silicone sealant.*

**Physical / chemical properties:**

**Silicone remover:**

- Colour: *Brown*
- Consistency: *Tixotropic paste*
- Specific gravity: *Approx. 0,85 kg/ltr*
- Shelf life: *Minimum 12 months in unopened tube if stored cool.*
- Packaging:

Art. no.	Size
9050	80 ml tube



## Directions for use:

### Preparation:

The surfaces must be **completely** dry and degreased.

Due to the risk of discolouration or dissolving of adjacent materials, it is always recommended to carry out a compatibility test. This is particularly important on plastic and painted / lacquered surfaces.

### Application:

The Silicone Remover is applied in a layer of approx. 5 mm on the silicone sealant which should be removed.

### Waiting time:

After 3 – 12 hours the silicone is dissolved and can be removed with a scraper. The surface is rinsed with water and wiped with a dry cloth. The time is dependant on the surface and tests should always be carried out in order to determine the necessary waiting time. If the silicone is not removed completely the first time, the process is repeated.

The following times can be considered as a guideline, but depends on the surface and the type of silicone:

1 mm sealant: max. 5 hours  
2 mm sealant: approx. 5 – 7 hours  
5 mm sealant: approx. 12 hours

If the sealant is thicker than approx. 5 mm it is recommended to remove it mechanically, where after remnants are removed with Silicone Remover 911. In other cases the silicone remover must be applied multiple times.

### Fungus:

If small areas with fungus should be removed, a waiting time of approx. 4 hours is recommended. After removal of the desired layer of sealant, it should be checked that the remaining sealant is intact. If not, another application of sealant is necessary.

## Health and safety:

### Hazard symbol:

*Xi*, Irritant  
*F*, Highly flammable

### Risk and Safety phrases:

*Highly flammable. Irritating to eyes and skin. Keep out of reach of children. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. This material and its container must be disposed of in a safe way. Wear suitable gloves and eye/face protection. If swallowed, seek medical advice immediately and show this container or label.*

For further information concerning safety, refer to Safety Data Sheet.

The information and data contained in this Product Information sheet are based on extensive laboratory testing and our practical experiences, and are meant for helping the user to find optimum working methods. As the conditions at the user are beyond our control, we make no warranties concerning the results, achieved by the products. The information's in this Product Information sheet are typical values, intended as a guideline. They should not be regarded as product specifications. Please also refer to our standard sales conditions and terms of delivery.

**DANA LIM A/S - KØBENHAVNSVEJ 220 - DK-4600 KØGE – DENMARK – INFO@DANALIM.DK**  
**PH. (+45) 56 64 00 70 - TELEFAX (+45) 56 64 00 90 - TECHNICAL SERVICE PH. (+45) 56 64 00 75**